



## INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification<sup>6</sup>:D21H 13/40, 17/49, 25/06, D06N 5/00,  
E04D 5/02, D21H 17/37

A1

(11) International Publication Number:

WO 99/13154

(43) International Publication Date:

18 March 1999 (18.03.99)

(21) International Application Number: PCT/US98/18354

(22) International Filing Date: 3 September 1998 (03.09.98)

(30) Priority Data:

08/925,890

8 September 1997 (08.09.97)

US

(71) Applicant: ELK CORPORATION OF DALLAS [US/US];  
Suite 1000, 14643 Dallas Parkway, Dallas, TX 75240 (US).(72) Inventor: HEINE, Darrell; 5007 Lake View Drive, Ennis, TX  
75119 (US).(74) Agents: MURNANE, John, D. et al.; Baker & Botts, LLP, 30  
Rockefeller Plaza, New York, NY 10112-0228 (US).(81) Designated States: AL, AM, AT, AU, AZ, BA, BB, BG, BR,  
BY, CA, CH, CN, CU, CZ, DE, DK, EE, ES, FI, GB, GE,  
GH, GM, HR, HU, ID, IL, IS, JP, KE, KG, KP, KR, KZ,  
LC, LK, LR, LS, LT, LU, LV, MD, MG, MK, MN, MW,  
MX, NO, NZ, PL, PT, RO, RU, SD, SE, SG, SI, SK, SL, TJ,  
TM, TR, TT, UA, UG, UZ, VN, YU, ZW, ARIPO patent  
(GH, GM, KE, LS, MW, SD, SZ, UG, ZW), Eurasian patent  
(AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent  
(AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT,  
LU, MC, NL, PT, SE), OAPI patent (BF, BJ, CF, CG, CI,  
CM, GA, GN, GW, ML, MR, NE, SN, TD, TG).

Published

*With international search report.*

(54) Title: STRUCTURAL MAT MATRIX

(57) Abstract

A structural mat matrix comprises (a) a substrate which consists essentially of from 80 % to 99 % by weight fiberglass fibers and from 20 % to 1 % by weight wood pulp and (b) a binder which consists essentially of from 80 % to 95 % by weight urea formaldehyde and from 20 % to 5 % by weight acrylic copolymer. The binder bonds the substrate fiberglass fibers and wood pulp together and comprises from 5 % to 15 % by weight of said matrix, preferably 10 % by weight of the matrix.

**FOR THE PURPOSES OF INFORMATION ONLY**

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AL	Albania	ES	Spain	LS	Lesotho	SI	Slovenia
AM	Armenia	FI	Finland	LT	Lithuania	SK	Slovakia
AT	Austria	FR	France	LU	Luxembourg	SN	Senegal
AU	Australia	GA	Gabon	LV	Latvia	SZ	Swaziland
AZ	Azerbaijan	GB	United Kingdom	MC	Monaco	TD	Chad
BA	Bosnia and Herzegovina	GE	Georgia	MD	Republic of Moldova	TG	Togo
BB	Barbados	GH	Ghana	MG	Madagascar	TJ	Tajikistan
BE	Belgium	GN	Guinea	MK	The former Yugoslav Republic of Macedonia	TM	Turkmenistan
BF	Burkina Faso	GR	Greece	ML	Mali	TR	Turkey
BG	Bulgaria	HU	Hungary	MN	Mongolia	TT	Trinidad and Tobago
BJ	Benin	IE	Ireland	MR	Mauritania	UA	Ukraine
BR	Brazil	IL	Israel	MW	Malawi	UG	Uganda
BY	Belarus	IS	Iceland	MX	Mexico	US	United States of America
CA	Canada	IT	Italy	NE	Niger	UZ	Uzbekistan
CF	Central African Republic	JP	Japan	NL	Netherlands	VN	Viet Nam
CG	Congo	KE	Kenya	NO	Norway	YU	Yugoslavia
CH	Switzerland	KG	Kyrgyzstan	NZ	New Zealand	ZW	Zimbabwe
CI	Côte d'Ivoire	KP	Democratic People's Republic of Korea	PL	Poland		
CM	Cameroon	KR	Republic of Korea	PT	Portugal		
CN	China	KZ	Kazakhstan	RO	Romania		
CU	Cuba	LC	Saint Lucia	RU	Russian Federation		
CZ	Czech Republic	LI	Liechtenstein	SD	Sudan		
DE	Germany	LK	Sri Lanka	SE	Sweden		
DK	Denmark	LR	Liberia	SG	Singapore		
EE	Estonia						

## STRUCTURAL MAT MATRIX

### SPECIFICATION

#### BACKGROUND OF INVENTION

This invention relates to a structural mat matrix such as a roofing  
5 shingle mat matrix.

For many years, structural articles such as roofing shingles have been comprised of fiberglass substrates coated with a binder which bonds together the fiberglass substrate fibers. Such substrates are nonwoven fiberglass mats which are desirable because they are lighter in weight than previously used mats. Fiberglass  
10 mats have also been preferred as roofing shingle substrates because of their fire resistant nature, their resistance to moisture damage, their excellent dimensional stability, their resistance to curl with temperature changes, their resistance to rot and decay, and their ability to accept more highly filled asphalt coatings.

Heretofore, efforts to optimize fiberglass roofing shingle substrates  
15 have focused on attempts at improving their tear strength and tensile strength without unduly increasing the weight of the shingle. Heavier shingles and other structural articles are generally more expensive because of greater raw material and transportation costs. Operating within such weight/cost constraints, shingle manufacturers have found that, to improve tear strength, they had to sacrifice tensile  
20 strength and vice versa.

U.S. Patent No. 4,112,174 discloses a mat suitable in the manufacture of roofing products which includes monofilament glass fibers, glass fiber bundles and a relatively small amount of binder, e.g. binder which is 15% by dry weight of the mat. The mat has a weight of between approximately 2.00 and 2.40 lbs/100 square  
25 feet. U.S. Patent No. 4,242,404 discloses a glass fiber mat useful for roofing products which includes individual filament glass fibers and extended glass fiber elements and a binder applied in an amount of about 3% to 45% by weight of the finished mat. The

basis weight of the finished mat is described as being at least 1 lb./100 sq. ft and preferably about 2.0 to 3.0 lbs/sq. ft.

U.S. Patent No. 4,472,243 discloses sheet type roofing material for use in built-up roofing and in the manufacture of roofing shingles. Chopped glass fibers are dispersed in a slurry of cellulosic fibers and binder is added. According to the patent, the material comprises 10-60 wt % glass fibers of varying lengths, 15-80% wt % cellulosic fiber and 5-25% binder. The patent states that the proportions and sizes of cellulosic and glass fibers described therein "provide the desired balance of structural properties" in the material to render it "suitable as substrate for roofing material" to "meet the desired standards for mechanical strength and fire resistance." The patent further notes that the "[g]lass fiber content of the felt of the invention is important in controlling its porosity and skeletal structure. ... On the high end of glass fiber content the felt substrate tends to be porous with a high order of skeletal structure. Such a felt will uncontrollably absorb excessive amounts of asphaltic saturant at a very high rate during roofing shingle processing and this has a deleterious effect in the spread of flame test due to severe asphaltic filled coating slides."

Surprisingly, the applicant has found that by producing a mat having a relatively high fiberglass content and relatively low cellulosic component and binder contents, the mat matrix has the same physical properties (such as tensile strength) of more costly heavy weight mats, with substantially increased tear strength.

### SUMMARY OF THE INVENTION

The present invention is a structural mat matrix which comprises (a) a substrate which consists essentially of from 80% to 99% by weight fiberglass fibers and from 20% to 1% by weight wood pulp and (b) a binder which bonds together the fiberglass fibers and the wood pulp. The binder consists essentially of from 80% to 95% by weight urea formaldehyde resin and from 20% to 5% by weight acrylic copolymer. The binder comprises from 5% to 15% by weight of the matrix, preferably 10%.

In a preferred embodiment, (a) the substrate consists essentially of 95%

by weight fiberglass and 5% by weight wood pulp and (b) the binder consists essentially of 90% by weight urea formaldehyde resin and 10% by weight acrylic copolymer.

### DETAILED DESCRIPTION

5                   Structural articles of the present invention are useful as, inter alia, roofing shingle mats, built-up roofing mats, facer mats and base plysheets. Articles produced in accordance with the invention are lighter in weight yet possess the same physical properties of tearing strength, tensile strength, wet tensile strength, porosity, and bursting strength as their prior art counterparts. Moreover, the applicant's  
10   inventive structural mat matrices achieve those results with lower raw material costs.

                  The structural mat matrices of the present invention comprise (a) a substrate which consists essentially of from 80% to 99% by weight fiberglass fibers and from 20% to 1% by weight wood pulp and (b) a binder which consists essentially of from 80% to 95% by weight urea formaldehyde resin and from 20% to 5% by  
15   weight acrylic copolymer. The fiberglass fibers which may be used in the substrate of the invention include wet chopped, 1" to 1 1/2" length, 14 to 18 micron diameter fibers which may be obtained from Owens Corning Fiberglas, Schuller and PPG Industries, Inc. The wood pulp may be cellulose fibers, cellulose pulp, Kraft pulp, hardwood and softwood pulps which may be obtained from, e.g. International Paper  
20   Co., Rayonier, James River and Weyerhaeuser and other market pulp manufacturers.

                  The urea formaldehyde resin in the binder may be a latex of about 60% solids, such as Casco Resin C511 or Casco Resin FG-413F which may be obtained from Borden Chemical, Inc.. The acrylic copolymer may be vinyl acrylic copolymer of about 49% solids such as Franklin International Covinax 830 or Rohm and Haas  
25   Rhoplex GL-618. In a preferred embodiment, the binder comprises 10% by weight of the matrix.

                  Structural mat matrices made in accordance with this invention may be of any shape and may be used in a variety of products including roofing shingles, built-up roofing, <sup>sheets</sup> facers, etc. Preferably, such matrices are planar in shape.

Additionally, the structural matrices may be coated with a water repellant material. Two such water repellant materials are Aurapel 33R or Aurapel 391 available from the Auralux Corporation of Norwich, CT. Further, structural matrices made in accordance with the invention may be coated with an antifungal material such as Micro-Chek 11P, an antibacterial material such as Micro-Chek 11-S-160, a surface friction agent such as Byk-375, and/or a coloring dye such as T-1133A.

The materials used in the making of the matrices and the methods of their preparation are described respectively in the following trade literature:

International Paper ALBACEL product literature for bleached southern pine pulp available from International Pulp Sales, 2 Manhattanville Rd., Purchase, N.Y. and International Paper SUPERCELL AO-2 product literature 0047 - 3/97 for fully bleached hardwood kraft pulp available from International Pulp Sales, 1290 Avenue of the Americas, New York, N.Y.; Owens Corning Product Bulletin 786 WUCS (Wet Use Chopped Strands) c. 1995 Owens Corning World Headquarters, Fiberglas Tower, Toledo, Ohio; PPG 8239 WET CHOPPED STRAND bulletin 2.3.1, Revised 2/95, PPG Fiberglass Products, One PPG Place, Pittsburgh, PA; Borden Casco Resin C511 DATA SHEET TDS XA-C511 06/97 and Resin FG-413F DATA SHEET TDS XA-413F 11/96, North American Resins Worldwide Packaging and Industrial Products (Div. of Borden Inc.) 520 112<sup>th</sup> Ave., N.E. Bellevue, WA; Franklin International Covinax 830 Data Sheet 3/20/95, Franklin International, 2020 Bruck Street, Columbus, OH; Rohm and Haas Rhoplex GL-618 product literature 20N2, September 1994, Rohm and Haas Co., Charlotte, N.C. The disclosures of each of the aforementioned trade publications are incorporated herein by reference.

#### EXAMPLE I

The applicant developed a structural mat matrix with physical performance characteristics of heavy weight mats achieved at lower basis weight by increasing the fiberglass content of the mat relative to the normal binder content and including a relatively minor amount of wood pulp in the substrate matrix. The matrix was produced as follows:

### Laboratory Preparation of Matrix

A 12" x 12" Williams Sheet Mold, equipped with a Lightnin mixer mounted on the top rim, was filled with approximately 5 gallons of softened water. Agitation was started and 10 ml. of Nalco 2388 viscosity modifier and 5 ml. of dilute dispersant were added. 5.94 grams of Owens-Corning 786 1" "M" chopped fiber glass (16 micron) were added and mixing continued for 12 minutes. 0.31 gram of International Paper AO2 Supercell wood pulp was dispersed for 15 seconds in a Waring blender containing 300 ml. of water. The pulp slurry was added to the sheet mold, the water drained and the web formed on the wire at the bottom of the sheet mold. After opening the sheet mold, a more open mesh wire was placed on top of the web, which was transferred and passed over a vacuum slot to remove excess water.

The web was transferred to a third wire and dipped in a rectangular pan containing a 90:10 by weight (solids) mixture of Borden Casco C-511X urea-formaldehyde resin and Franklin International Covinax 830 acrylic latex at 14% total solids. The supported web was passed over a vacuum slot to remove excess saturant and then placed in a circulating air oven set at 400°F for 2 minutes for drying and curing.

### Laboratory Preparation of Shingle Coupon

The filled asphalt coating compound was prepared by heating 350 grams of Trumbull oxidized asphalt in a one-quart sample can equipped with a high-speed mixer and an electrically-heated mantle. When the asphalt temperature reached 400°F, 650 grams of JTM Alsil-04TR fly ash were added slowly with agitation until a uniform blend was obtained.

Precut (7½" x 11") release paper was placed in a Pacific-Scientific draw down apparatus. A piece of matrix was mounted on the release paper using transparent tape and the draw down skimmer gauge set to 45 mil (0.045 inch). Hot coating compound (400°F) was poured in front of the knife, the electric drive turned on and the knife drawn across the length of the matrix sample. Excess coating was removed from the knife and the catch pan. The sample was removed from the apparatus and remounted asphalt side down on a fresh piece of release paper. The skimmer gauge was set to 90 mil (0.090 inch) and the reverse side coated with asphalt

compound in the same manner as above.

After cooling to ambient temperature, the coupon, sandwiched between sheets of release paper, was placed in a Carver press, having platens preheated to 250°F, and was pressed at a pressure of 1000 pounds per square inch for 30 seconds, resulting in a final coupon thickness of about 65 mil. (0.065 inch).

#### EXAMPLES II TO VII

Laboratory handsheet-matrix samples were prepared by the same procedure described above for Example I, using the substrate compositions listed in Table 1, the binder compositions listed in Table III and matrix compositions listed in Table V, with the quantities of each raw material calculated to obtain the matrix basis weights listed for each example in Table V.

Example II of the instant invention is a modification of Example I, with the portion of wood pulp in the substrate increased to 10%. Example III is a modification of Example I, in which the binder is 100% urea formaldehyde resin. Example IV is a modification of Example I, having 15% acrylic copolymer resin content in the binder. Example V is a modification of Example I, with no wood pulp in the substrate. Examples VI and VII are matrix samples of conventional composition having basis weights of about 1.4 and 1.8 lb/sq. respectively, to serve as controls.

Single coupons were prepared in an identical manner to that described above for Example I.

#### EXAMPLES VIII AND IX

Rolls of matrix used in these examples were prepared using conventional paper making equipment commonly used in the roofing mat industry. Binder was added in line with conventional wet-web impregnation equipment. Drying and curing of the matrix rolls were accomplished with gas-fired ovens.

Example VIII is the preferred matrix of the instant invention. Example IX is a standard matrix of higher basis weight and binder content used in the production of shingles and is included to serve as a control.

Shingles were made using conventional roofing shingle production equipment and raw materials and contained granules.



## PHYSICAL PROPERTIES

- Properties of the matrix samples and shingle coupons of Examples I to VII are shown in Table VII. Those of the production matrixes and shingles of Examples VIII and IX are listed in Table VIII. Standard testing procedures as
- 5 published by the Technical Association of the Pulp and Paper Industry (Tappi) and the American Society of Testing and Materials (ASTM) with modifications adopted by the roofing industry were used, as described below.

### PROCEDURE A

- Basis weight of the structural mat matrix was measured according to
- 10 TAPPI Method T 1011 om-92 using a 10"x10" test specimen cut from a handsheet. The value is reported in pounds per square (100 square feet), as is customary in the roofing industry.

### PROCEDURE B

- Loss on ignition of the structural mat matrix was tested by TAPPI
- 15 Method T 1013 om-92; the results being reported as a percentage of the initial matrix weight.

### PROCEDURE C

- Tensile strength of the structural mat matrix was measured according to ASTM D-828. Jaw width and sample width were both 3 inches; initial gap
- 20 between jaws was 3 inches; rate of jaw separation was 12 inches per minute, test results are reported in pounds per 3"-wide sample.

### PROCEDURE D

- Tear resistance of the structural mat matrix was measured according to TAPPI Method T 1006 sp-92, using the Elmendorf tearing tester described in TAPPI
- 25 Method T 414. A single-ply sample was tested. The results are reported in grams.

### PROCEDURE E

- Tensile strength of the shingle coupon was tested according to ASTM D-828. Jaw width and sample width were both 2 inches; initial gap between jaws was 3 inches; rate of jaw separation was 2 inches per minute. Test results are reported in
- 30 pounds per 2"-wide sample.

PROCEDURE F

Tearing resistance of the shingle coupon was measured according to ASTM D-3462 using an Elmendorf tearing tester. Test results are reported in grams.

TABLE I

Formulation of Laboratory Handsheet Substrate  
(Percent by Weight)

	Ex. I	Ex. II	Ex. III	Ex. IV	Ex. V	Ex. VI	Ex. VII
Fiberglass	95.0	90.0	95.0	95.0	100.0	100.0	100.0
Wood Pulp	5.0	10.0	5.0	5.0			
Dispersant	0.025	0.025	0.025	0.025	0.025	0.025	0.025
Viscosity Modifier	0.013	0.013	0.013	0.013	0.013	0.013	0.013

TABLE II

Formulation of Production Substrate  
(Percent by Weight)

	Ex. VIII	Ex. IX
Fiberglass	95.0	100.0
Wood Pulp	5.0	
Dispersant	0.025	0.025
Viscosity Modifier	0.013	0.013

TABLE III

Formulation of Laboratory Handsheet Binder  
(Percent by Dry Weight)

	Ex. I	Ex. II	Ex. III	Ex. IV	Ex. V	Ex. VI	Ex. VII
5 Borden FG-413F						95.0	95.0
Borden C-511X	90.0	90.0	100.0	85.0	90.0		
10 Rohm & Haas GL-618						5.0	5.0
Franklin Covinax 830	10.0	10.0		15.0	10.0		

TABLE IV

15 Formulation of Production Binder  
(Percent by Dry Weight)

	Ex. VIII	Ex. IX
Borden FG-413F		95.0
Borden C-511X	90.0	
Rohm & Haas GL-618		5.0
20 Franklin Covinax 830	10.0	

TABLE V

## Laboratory Handsheet Matrix Composition &amp; Basis Weight

	Ex. I	Ex. II	Ex. III	Ex. IV	Ex. V	Ex. VI	Ex. VII
Substrate Portion (%)	90.0	90.0	90.0	90.0	90.0	80.0	80.0
Binder Portion (%)	10.0	10.0	10.0	10.0	10.0	20.0	20.0
Basis Wt. (lb/100 ft <sup>2</sup> )	1.45	1.43	1.45	1.44	1.45	1.42	1.80

TABLE VI

## Production Matrix Composition &amp; Basis Weight

	Ex. VIII	Ex. IX
Substrate Portion (%)	90.0	80.0
Binder Portion (%)	10.0	20.0
Basis Wt. (lb/100 ft <sup>2</sup> )	1.44	1.60

TABLE VII

## Physical Properties of Laboratory Matrix Samples and Laboratory Shingle Coupons

		Proce- dure	Ex. I	Ex. II	Ex. III	Ex. IV	Ex. V	Ex. VI	Ex. VII
	MAT MATRIX								
5	Basis Weight	A	1.45	1.43	1.45	1.44	1.45	1.42	1.78
	Loss on Ignition	B	15.5	18.7	14.7	14.0	11.1	20.4	19.6
10	Tensile Strength	C	97	91	73	85	110	112	130
	Tearing Resist- ance	D	398	387	436	429	401	203	239
15	SHINGLE COUPON								
	Tensile Strength	E	170	135	137	155	172	156	178
	Tearing Resistance	F	1309	918	967	1076	958	836	843

TABLE VIII

## Physical Properties of Production Matrix and Production Shingles

		Procedure	Ex. VIII	Ex. IX
	MATRIX			
	Basis Weight	A	1.43	1.60
5	Loss on Ignition	B	15.5	21.1
	Tensile Strength -Machine Direction	C	85	81
	Tensile Strength -Cross Direction		28	45
10	Tearing Resistance -Machine Direction	D	344	311
	Tearing Resistance -Cross Direction		408	429
	SHINGLE			
15	Tensile Strength -Machine Direction	E	178	151
	Tensile Strength -Cross Direction		80	91
20	Tearing Resistance -Machine Direction	F	1167	1103
	Tearing Resistance -Cross Direction		1392	1123

Surprisingly, the applicant has discovered that by reducing the binder content and increasing the overall fiber amount and including a relatively minor amount of wood pulp, the desired weight of the mat can be achieved while dramatically improving tear strength of the matrix and the shingle produced from the matrix. Although not wishing to be bound by any particular theory, the applicant believes that the wood pulp cellulosic component of the matrix in the invention bridges the glass fibers to enhance tensile strength, thereby permitting a decrease in binder content and an increase in fiberglass content to provide the surprising results noted in Tables VII and VIII above.

It should be understood that the above examples are illustrative, and that components other than those described above can be used while utilizing the principles underlying the present invention. For example, other sources of wood pulp as well as mixtures of urea formaldehyde and/or acrylic latices can be used in formulating the matrices. Other suitable types of latex can be used in combination with urea formaldehyde to improve the properties of the matrices, provided that fiberglass comprises the major proportion of the matrix. The matrices can be employed in roofing materials such as roofing shingles, built-up roofing, rolled roofing and other products such as facer, etc.

CLAIMS

1. A structural mat matrix which comprises:
  - a) a substrate which consists essentially of from 80% to 99% by weight fiberglass fibers and from 20% to 1% by weight wood pulp; and
  - 5        b) a binder which consists essentially of from 80% to 95% by weight urea formaldehyde resin and from 20% to 5% by weight acrylic copolymer; wherein said binder bonds the substrate fiberglass fibers and wood pulp together and wherein said binder comprises from 5% to 15% by weight of said matrix.
- 10        2. A structural mat matrix according to claim 1 wherein said binder comprises 10% by weight of said matrix.
3. A structural mat matrix according to claim 2 which comprises
  - a) a substrate which consists essentially of 95% by weight fiberglass and 5% by weight wood pulp; and
  - 15        b) a binder which consists essentially of 90% by weight urea formaldehyde resin and 10% by weight acrylic copolymer.
4. A structural mat matrix according to claim 3 in which said acrylic copolymer is a vinyl acrylic copolymer.
5. A method of making a structural mat matrix which comprises
  - 20        a) forming a wet mat which consists essentially of from 80% to 99% by weight fiberglass fibers and from 20% to 1% by weight wood pulp;
  - b) applying a binder which consists essentially of from 80% to 95% by weight urea formaldehyde resin and from 20% to 5% by weight acrylic copolymer; and
  - 25        c) drying and curing said mat and binder at elevated temperatures.



6. A roofing product which comprises:

a) a structural mat matrix which comprises:

i) a substrate which consists essentially of from 80% to 99% by weight fiberglass fibers and from 20% to 1% by weight wood pulp; and

5 ii) a binder which consists essentially of from 80% to 95% by weight urea formaldehyde resin and from 20% to 5% by weight acrylic copolymer;

wherein said binder bonds the substrate fiberglass fibers and wood pulp together and wherein said binder comprises from 5% to 15% by weight of said matrix; and

10 b) a filled asphalt which impregnates and/or coats the mat matrix.

# INTERNATIONAL SEARCH REPORT

Information on patent family members

International Application No

PCT/US 98/18354

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
US 4472243 A	18-09-1984	CA 1236658 A	17-05-1988
US 4242404 A	30-12-1980	AU 535254 B	08-03-1984
		AU 5736880 A	20-11-1980
		CA 1137731 A	21-12-1982
		DK 185780 A	17-11-1980
		EP 0019465 A	26-11-1980
		FI 801495 A	17-11-1980
US 4112174 A	05-09-1978	NONE	
EP 0025115 A	18-03-1981	US 4269886 A	26-05-1981
		US 4284470 A	18-08-1981
		AT 4653 T	15-09-1983
		CA 1147541 A	07-06-1983

# INTERNATIONAL SEARCH REPORT

International Application No.

/US 98/18354

## A. CLASSIFICATION OF SUBJECT MATTER

IPC 6 D21H13/40 D21H17/49 D21H25/06 D06N5/00 E04D5/02  
D21H17/37

According to International Patent Classification (IPC) or to both national classification and IPC

## B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

IPC 6 D21H D06N E04D

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

## C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	US 4 472 243 A (BONDOC ALFREDO A ET AL) 18 September 1984 cited in the application ---	
A	US 4 242 404 A (BONDOC ALFREDO A ET AL) 30 December 1980 cited in the application ---	
A	US 4 112 174 A (HANNES GEORGE JOHN ET AL) 5 September 1978 cited in the application ---	
A	EP 0 025 115 A (GAF CORP) 18 March 1981 -----	

☐ Further documents are listed in the continuation of box C.



Patent family members are listed in annex.

\* Special categories of cited documents:

"A" document defining the general state of the art which is not considered to be of particular relevance

"E" earlier document but published on or after the international filing date

"L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)

"O" document referring to an oral disclosure, use, exhibition or other means

"P" document published prior to the international filing date but later than the priority date claimed

"T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

"X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone

"Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.

"&" document member of the same patent family

Date of the actual completion of the international search

7 December 1998

Date of mailing of the international search report

14/12/1998

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2  
NL - 2280 HV Rijswijk  
Tel. (+31-70) 340-2040, Tx. 31 651 epo nl,  
Fax: (+31-70) 340-3016

Authorized officer

Leroy, A.